

WHAT IS CLAIMED IS:

1. A method for fabricating ceramic nanocomposite powder, said method comprising:

- (a) dispersing carbon nanotubes in a dispersion medium;
- (b) sonicating the dispersion;
- (c) dispersing a water-soluble salt in the sonicated dispersion of (b);
- (d) sonicating the dispersion of (c); and
- (e) drying and calcinating the sonicated dispersion of (d),

wherein said water soluble salt forms a ceramic matrix post-calcination;

thereby fabricating ceramic nanocomposite powder, wherein said carbon nanotubes are homogeneously dispersed in said ceramic matrix.

2. The method according to claim 1, wherein said dispersion medium in (a) is selected from the group consisting of water, ethanol, nitric acid solution, toluene, N,N-dimethylformamide, dichlorocarbene and thionyl chloride.

3. The method according to claim 1, wherein said water-soluble salt, mixed with the carbon nanotubes, includes metal-based salts capable of being formed into a ceramic matrix prior to calcination.

4. The method according to claim 1, wherein said ceramic matrix is selected from the group consisting of aluminum oxides, copper oxides, cobalt oxides, nickel oxides, zinc oxides, tungsten oxides and silicon oxides.

5. The method according to claim 3, wherein said ceramic matrix is selected from the group consisting of aluminum oxides, copper oxides, cobalt oxides, nickel oxides, zinc oxides, tungsten oxides and silicon oxides.

6. The method according to claim 1, wherein said drying is carried out at 80-100°C.

7. The method according to claim 1, wherein when said ceramic matrix requires a calcination temperature of 400°C or lower, the calcination is carried out in air at 300-350°C.

8. The method according to claim 1, wherein when said ceramic matrix requires a calcination temperature of 400°C or higher, the calcination is carried out under high vacuum at a temperature of 400-1,700°C.

9. The method according to claim 6, wherein when said ceramic matrix requires a calcination temperature of 400°C or lower, it is further dried at 300-350°C.